

SureTac™ White

Mounting Adhesive

SureTac™ White is a 1.4 mil (36µ) white PP film coated on both sides with a pressure sensitive, high shear, acid-free solvent acrylic adhesive that is protected by a moisture stable bleached Kraft differential release paper coated on both sides with siliconized PE. The adhesive is self-wound on the release liner.

Typical Applications

- Compatible with a wide variety of media and substrates.
- Its solvent acrylic adhesive offers a stable and permanent bond for outdoor use.
- White carrier blocks show-through on dark substrates.
- UV resistant.
- Has a high bond strength to media and substrates such as polyester and polycarbonate.

Product Structure

Adhesive	Solvent Acrylic (Pressure Sensitive)	3.6 mil (92µ)
Film	White PP	
Adhesive	Solvent Acrylic (Pressure Sensitive)	
Release Paper	2 Side PE Coated Bleached Kraft Differential Release Paper	

Physical Characteristics

Film Thickness	1.4 mil (36µ)
Adhesive Layer	1.1 mil (28µ) on each side
Film/Adhesive Ratio	1.1:1.4:1.1
UV Protection Factor	UV Resistant
Outdoor Durability	1 year
Service Temperature Range	-30°F to 220°F (-34°C to 104°C)
Shelf Life	Use within 1 year after opening original box
Storage Conditions	59°F to 72°F (15°C to 22°C); 50 - 55% Relative Humidity

Process Settings

Equipment Type	Temperature	Speed
Roller Laminator	Room temperature to 100°F (38°C)	1 ft to 8 ft (0.3m to 2.5m) per minute
Press	Not recommended	

IMPORTANT NOTE:

Information is intended only as a guide and is given without guarantees. Purchasers should independently determine, prior to use, the suitability of each material for their specific purpose. Follow the indications on the package, ask for the safety data sheets and always follow the indications contained therein.

Only the correct use of the product will allow satisfactory results. For this reason, Drytac is not responsible for improper use of the product, either by application or substrate applied to. Make certain that product is right for the desired use, and work according to the instructions given in our technical data sheets. If in doubt of the appropriate application methods or use, contact Drytac at one of the phone numbers listed below.